


2420,Yurigaoka 1-chome, Moriya-City, Ibaraki
3020110, Japan
E-mail information@chemical-suzuhiro.co.jp
http://www.chemical-suzuhiro.co.jp

PRODUCT

Fire Cut P-65CN (FCP-65CN)

1-1

CHEMICAL STRUCTURE



CHEMICAL NAME

Bis [3,5-dibromo-4- (2,3-dibromopropoxy) phenyl] sulfone
CAS No. 42757-55-1

PROPERTIES

Appearance	White Powder
Bromine Content	ca. 65%
Melting Point	ca. 105°C
Volatiles	≤ 0.3%

APPLICATION

Polyethylene, Polypropylene, Polystyrene

PACKAGE

25kg net paper bag

FORMULATION

PP		96.0	88.0
FCP-65CN		3.0	9.0
FCP-AT-3 ^{CN} (Sb ₂ O ₃)		1.0	3.0
UL94	3.0mm	V2	V0
	1.5mm	V2	V0